

Pavements

Asphalt

Crack Sealant, Rubberized Asphalt, Hot Poured

List # 3.05.40

Page 1 of 1

Date: 01-Aug-2018

CUSTODIAL OFFICE : MERO - Bituminous - (416) 235-3715

NOTES:

- Pour Temperature is in degrees Celsius.

- For all products shown, method of application is either by pressure or gravity feed.

- For the purposes of this DSM, "Southern Ontario" is defined as Central Region, Southwestern Region, Ottawa District - west of Highway 416 from Johnstown to Kemptville and then south of Highway 43 from Kemptville to Perth and Bancroft District - south of Highway 7 from Perth to Maberly then south of a line drawn from Maberly to Kinmount.

Company	Product Name	Pour Temperature (°C)	Area Use
Crafco Inc. (Crafco Way) 6975 W Crafco Way Chandler AZ 85226 2505 USA Tel: 602-276-0406 Fax: 480-961-0513 Web: www.crafco.com Ontario Source: Crafco, Inc. (ON) 66 Akron Rd Toronto (Etobicoke) ON M8W 1T2 Canada Tel: 800-528-8242 Email: sales@crafco.com Web: www.crafco.com	ROADSAVER #211 (34211)	190 - 210	Southern Ontario
	ULTRASEAL 1190	190 - 205	Southern Ontario
	ULTRASEAL 3405	180 - 200	All MTO Districts
	ULTRASEAL 3407 LM	175 - 190	All MTO Districts
	Deery 103GL	193 - 204	Southern Ontario
McAsphalt Industries Ltd. 8800 Sheppard Avenue East Toronto ON M1B 5R4 Tel: 416-281-8181 Fax: 416-281-8842 Toll Free: 800-268-4238 Email: info@mcasphalt.com Web: www.mcasphalt.com	MACSEAL 6690-4 MOD (Previous Name: BERAM LM 3060)	170 - 200	All MTO Districts
	MACSEAL 6690-1 (Previous Name: BERAM 190)	180 - 200	Southern Ontario
	MACSEAL BDM (Previous Name: BEMALASTIC 1213 BDM)	180 - 195	Southern Ontario
Right Pointe Company P.O. Box 467, 234 Harvestore Drive DeKalb IL 60115-8604 United States Tel: 815-754-5700 Fax: 815-754-5702 Email: patrickg@rightpointe.com Web: www.rightpointe.com	RP Type 1 MV	185 - 200	Southern Ontario