

**Structural
Coatings**
Paint Coating Systems for Galvanized Surfaces

List # 9.20.60
Page 1 of 1
Date: 01-Aug-2018

CUSTODIAL OFFICE : Bridge Office - (905) 704-2406

Notes:
DFT - Dry Film Thickness.

Company	Product System	Coat #	Coating Identity	Coating Colour	Thinner	Minimum DFT (µm)
Carboline Canada 95 Sunray Street Whitby ON L1N 9C9 Canada Tel: 800-263-3112 Fax: 800-786-6329 Office: 905-430-3333 Email: canada@stoncor.com Web: www.carboline.ca	Modified Aluminum Epoxy Mastic / Aliphatic Polyurethane	1st	Carbomastic 15FC	Red M500	Carboline 2	125
	Modified Aluminum Epoxy Mastic / Aliphatic Polyurethane	2nd	Carbothane 134 HG, Note: only material produced by the rapid tint process is allowed.	Grey 4750	Carboline 25	50
PPG Canada Inc. 8200 Keele Street Concord ON L4K 2A5 Canada Tel: 905-738-7310 Fax: 905-669-3486 Cellular: 416-347-9533 Email: dennis.oreilly@ppg.com Web: www.ppgpmc.com	High Build Epoxy / Aliphatic Polyurethane	1st	Amercoat 385	White WH-01	Amercoat 7, 65 or 101	100
	High Build Epoxy / Aliphatic Polyurethane	2nd	Amercoat 450H	U.S. Fed. Std. 16307 Grey	Amercoat 65 or 101	75
Ontario Source: Sherwin-Williams Company 418 North Service Rd. E, Suite 1A Oakville ON L6H 5R2 Canada Tel: 905-849-2921 Fax: 905-849-2926 Cellular: 416-676-2954 Email: mharman@sherwin.com Web: www.sherwin.com	High Build Epoxy / Aliphatic Polyurethane	1st	Macropoxy 646 FC	Mill White	R7K15 or R7K111	125
	High Build Epoxy / Aliphatic Polyurethane	2nd	Acrolon 218 HS	U.S. Fed. Std. 16307 Grey	R7K15, R6K10 or R7K111	75